



Formkonstanten
core factors

Formfaktor core factor	$C_1 = 0,71 \text{ mm}^{-1}$
Eff. magn. Weglänge eff. magn. path length	$l_e = 61,4 \text{ mm}$
Eff. magn. Querschnitt eff. magn. cross section	$A_e = 86,8 \text{ mm}^2$
Eff. magn. Volumen eff. magn. volume	$V_e = 5350 \text{ mm}^3$
Gewicht weight	$G \approx 25,5 \text{ g}$

Material material	A_L -Wert A_L value	Toleranz / tolerance		Bestellnummer* order number*
		unbeschichtet uncoated	beschichtet coated	
K 2006	3700 nH	± 25 %	± 25 %	xxx 271415 026
K 4000	7100 nH	± 25 %	± 25 %	xxx 271415 004
K 5500	9750 nH	± 25 %	± 25 %	xxx 271415 055
K 6000	11150 nH	± 25 %	± 30 %	xxx 271415 006
K 7000	12100 nH	± 25 %	± 30 %	xxx 271415 007

xxx siehe Seite 263
xxx see page 263